

T-Bentostop

WATERSTOP



DESCRIPTION

Bentonite swellable waterstop ideal to seal vertical and horizontal concrete construction joints and to seal penetrations which are embedded in concrete. No fixing mesh required.

APPLICATIONS

Casting resumption sealing.

tol.

TECHNICAL DATA SHEET

Physical/mechanical properties

Sodic bentonite	75%
Organic bond	25%
Specific weight	1,65 g/m ³
Confined expansion swelling test	25 g/m ²
Swelling in contact with water (after 14 days)	>425%
Maximum deflection	No tearing with 180° angle inflection
Elongation at break	141%
Working temperature	-30/+60 °C
Suitable for direct contact with drinking water	Yes

Dimensions

Cross section	20x25 mm
Length	5 m
Rolls per box	6
Length per box	30 m
Boxes per pallet	30

Storage: cool and dry, protect against sunlight, use within 24 months after receipt.

The information given in this data sheet is to the best of our knowledge true and correct. TeMa srl reserves the right to change its product specifications at any time. It is the responsibility of the specifier and purchaser to ensure that product specifications used for design and procurement purposes are current and consistent with the products used in each instance.

TeMa Technologies and Materials s.r.l.

Via dell'Industria, 21 - 31029 Vittorio Veneto (TV) - Tel. +39 0438 50 31 - Fax +39 0438 50 34 60
www.temacorporation.com - email: info@temacorporation.com