

K-Roof C 10 EP

UNDERLAY FOR DISCONTINUOUS ROOFING



DESCRIPTION

Draining and separating layer made of a monofilament wire mesh.

APPLICATIONS

Under metal roofs.

tol.

TECHNICAL DATA SHEET

Raw material (+ UV stabilizer)		PP	
Thickness	(EN 1849-2)	9 mm	±15%
Mat weight	(EN 1849-2)	350 g/m ²	±10%
Tensile strength MD	(EN 12311-1/EN 13859-1 Anx. A)	60 N/5cm	±15%
Tensile strength CMD	(EN 12311-1/EN 13859-1 Anx. A)	25 N/5cm	±10%
Reaction to fire	(EN 13501-2)	E class	
Working temperature		-20 / +80 °C	
UV Stability		3 months	

Dimensions

Roll width	(EN 1848-2)	1,4 cm	±2%
Roll length	(EN 1848-2)	25 m	±2%
Rolls per pallet		9	

MD: Machine direction

CMD: Cross machine direction

Storage: cool and dry, protect against sunlight, use within 24 months after receipt.

The information given in this data sheet is to the best of our knowledge true and correct. TeMa srl reserves the right to change its product specifications at any time. It is the responsibility of the specifier and purchaser to ensure that product specifications used for design and procurement purposes are current and consistent with the products used in each instance.

TeMa Technologies and Materials s.r.l.

Via dell'Industria, 21 - 31029 Vittorio Veneto (TV) - Tel. +39 0438 50 31 - Fax +39 0438 50 34 60
www.temacorporation.com - email: info@temacorporation.com

K-Roof C 10 EP S

SPACER UNDER METALLIC ROOFING



DESCRIPTION

Draining and separating layer made of a monofilament wire mesh.

APPLICATIONS

Under metal roofs.

tol.

TECHNICAL DATA SHEET

Raw material (+ UV stabilizer)		PP	
Thickness	(EN 1849-2)	8 mm	±15%
Mat weight	(EN 1849-2)	300 g/m ²	±10%
Tensile strength MD	(EN 12311-1/EN 13859-1 Anx. A)	45 N/5cm	±15%
Tensile strength CMD	(EN 12311-1/EN 13859-1 Anx. A)	20 N/5cm	±10%
Reaction to fire	(EN 13501-2)	E class	
Working temperature		-20 / +80 °C	
UV Stability		3 months	

Dimensions

Roll width	(EN 1848-2)	1,4 cm	±2%
Roll length	(EN 1848-2)	30 m	±2%
Rolls per pallet		9	

MD: Machine direction

CMD: Cross machine direction

Storage: cool and dry, protect against sunlight, use within 24 months after receipt.

The information given in this data sheet is to the best of our knowledge true and correct. TeMa srl reserves the right to change its product specifications at any time. It is the responsibility of the specifier and purchaser to ensure that product specifications used for design and procurement purposes are current and consistent with the products used in each instance.

TeMa Technologies and Materials s.r.l.

Via dell'Industria, 21 - 31029 Vittorio Veneto (TV) - Tel. +39 0438 50 31 - Fax +39 0438 50 34 60
www.temacorporation.com - email: info@temacorporation.com

K-Roof C 10 Plus

SPACER UNDER METALLIC ROOFING



DESCRIPTION

Draining and separating layer made of a monofilament wire mesh.

APPLICATIONS

Under metal roofs.

tol.

TECHNICAL DATA SHEET

Raw material (+ UV stabilizer)		PP	
Thickness	(EN 1849-2)	9,5 mm	±15%
Mat weight	(EN 1849-2)	450 g/m ²	±10%
Tensile strength MD	(EN 12311-1/EN 13859-1 Anx. A)	70 N/5cm	±15%
Tensile strength CMD	(EN 12311-1/EN 13859-1 Anx. A)	40 N/5cm	±10%
Reaction to fire	(EN 13501-2)	E class	
Working temperature		-20 / +80 °C	
UV Stability		3 months	

Dimensions

Roll width	(EN 1848-2)	1,4 cm	±2%
Roll length	(EN 1848-2)	25 m	±2%
Rolls per pallet		9	

MD: Machine direction

CMD: Cross machine direction

Storage: cool and dry, protect against sunlight, use within 24 months after receipt.

The information given in this data sheet is to the best of our knowledge true and correct. TeMa srl reserves the right to change its product specifications at any time. It is the responsibility of the specifier and purchaser to ensure that product specifications used for design and procurement purposes are current and consistent with the products used in each instance.

TeMa Technologies and Materials s.r.l.

Via dell'Industria, 21 - 31029 Vittorio Veneto (TV) - Tel. +39 0438 50 31 - Fax +39 0438 50 34 60
www.temacorporation.com - email: info@temacorporation.com